

EPS® 2526

Styrenated Acrylic Emulsion

MARKET SEGMENT: CONSTRUCTION

COMMON APPLICATIONS: TOPCOAT

EPS® 2526 is a styrenated acrylic emulsion offering excellent hardness and wet/dry film clarity. Well suited for use in clear and pigmented finishes on cementitious substrates.

PERFORMANCE BENEFITS

- Hardness and block resistance
- Yellowing resistance
- Gloss and film clarity
- Blush resistance
- Chemical and “hot tire” resistance

TYPICAL PROPERTIES

Weight Solids	40.0 ± 0.7%
Weight/Gallon	8.70 ± 0.10
pH	7.5 – 8.5
Volume Solids	37.3 ± 0.7%
MFFT	> 60° C
Volatile(s)	Water

These typical properties do not represent specifications.

SUGGESTED COALESCING SOVENT(S)

(% Solvent on Binder Solids – Pass 40°F LTC Test)

Texanol	25-30%
DPnP	30-35%

SUGGESTED FORMULATIONS

- EPS® 2526 CLR BT1 - High Gloss Clear Topcoat
- EPS® 2526 CLR LS2 - Concrete Sealer / Dustproofers
- EPS® 2526 BT2 - Pigmented Concrete Sealer
- EPS® 2526 CS1 - Concrete Cure & Seal
- EPS® 2526 HS1 - High Solids Concrete Sealer